



EPOCHEMMIE CO., LTD

www.epochemmie.com

E-mail: sales@epochemmie.com epochemmie@163.com

DATA SHEET

Commodity: Gel Strong Acid Cation Exchange Resin **Type:** C004

For use in water softening applications

Applications: C004 is a high purity premium grade ,high capacity, gelular, sulfonated, polystyrene cation resin supplied in the sodium or hydrogen form as moist, tough, uniform, spherical beads. C004 is intended for use in all water softening, dealkalization, deionization and chemical processing applications, with excellent

Resistance to oxidation

Product Description:

Typical physical & Chemical characteristics

Polymer Matrix Structure	Styrene Crosslinked with DVB
Physical Form and Appearance	Clear spherical beads
Whole Bead Count	95% min.
Functional Groups	R-SO ₃ ⁻
Ionic Form ,as shipped	Na
Total Exchange Capacity, Na ⁺ form, wet, volumetric	2.20 eq/l min.
Moisture Retention, Na ⁺ form	40-46%
Particle Size Range	+1.2mm 5%max, -0.3mm 1%max
Swelling Na ⁺ →H ⁺	10% max.
Ca ²⁺ →Na ⁺	5% max.
Shipping Weight (approx.)	800-880 g/l
Specific Gravity, moist Na ⁺ Form	1.3
pH Range, Stability	0 - 14

Suggested Operating Condition

Maximum Temperature	
Na ⁺ Form	150°C (300°F) max.
H ⁺ Form	100°C (212°F) max.
Minimum Bed Depth	0.6m(24inches)
Backwash Rate	25 to 50% Bed Expansion
Regenerant Concentration	
Hydrogen Cycle	6% HCl or 4 to 8%H ₂ SO ₄
Sodium Cycle	4% to 6% NaCl
Regenerant Flow Rate	4 to 12 BV/h (0.5 to 1.5gpm/cu.ft.)
Regenerant Contact Time	At least 30 minutes
Regenerant Level	112 -300g/L (4 to 10 pounds/ cu.ft.)
Displacement Rinse Rate	Same as Regenerant Flow Rate
Displacement Rinse Volume	35 to 60 gallons/cu.ft.
Fast Rinse Rate	Same as Service Flow Rate
Fast Rinse Volume	35 to 60 gallons/cu.ft.
Service Flow Rate	10-25m/h (2 to 10 gpm/cu.ft.)